

GREEN INSULATION TECHNOLOGIES, LLC

11614 State Route 88

P.O. Box 6

2.0 Pound

Garrettsville, OH 44231

Plant (330) 527-3626

Fax (330) 527-3627

Product Description

GIT's 2.0 is non-ozone depleting spray polyurethane foam. GIT's 2.0 foam is a reaction product of polymeric isocyanate "A-component" and resin "B-component" blown by water. GIT's 2.0 is closed cell rigid foam with nominal 2.0 lb/ft³ density. Utilization of water as a blowing agent yields superior insulation properties over conventional insulating materials. GIT's 2.0 is designed for construction of the airtight, energy efficient buildings.

Equipment

GIT's 2.0 is designed for use with a 1:1 by volume proportioning unit equipped with heaters to maintain recommended material temperatures. The spray gun should be set up for 12-20lb's per minute throughput. Proper equipment and gun selection is critical to insure optimal processing characteristics. Contact a Green Insulation Technician for assistance in selecting proportioning units and guns.

Processing Temperature and Humidity

GIT's 2.0 may be applied between ambient temperatures of 50° F and 110° F and relative humidity less than 80%. DO NOT apply 2.0 if ambient temperature is less than 5° F above dew point.

Machine Pressure and Temperature Recommendations

	<u>Preheater</u>	<u>Pressure</u>
A side	120 - 130° F	1,000-1,200 PSI
B side	120 - 130° F	1,000-1,200 PSI
Hose Temp	120 - 130° F	

Application

Optimal application thickness is ½ to 2.0 inches. Lifts beyond 3" could result in excessive exotherm and possible scorching. GIT's 2.0 is designed for interior use and not approved for exterior applications.

Material Storage

GIT's 2.0 components MUST be stored between 50 –80 ° F and out of direct sunlight. The A component is moisture sensitive. If material remains in a drum be sure to seal bungs tightly to minimize moisture exposure.

Disposal of Empty Drums

Empty drums should be dripped dry, and may be sent to a qualified drum re-conditioner, drum recycling facility, or a land fill permitted to accept used drums. Drums should not be torched cut to avoid generation of irritating toxic gases and vapors from residual chemicals or cured product present in the drum.

Safety Precautions

Appropriate literature has been assembled which provides information concerning the health and safety precautions that must be observed when handling 2.0 components. Before working with these products, you must read and become familiar with the available information on their hazards, proper use, and handling. This can not be over emphasized. Information is available in several forms, e.g., material safety data sheets and product labels.

GIT's 2.0 must be covered by an improved 15 minute thermal barrier or ignition barrier, depending on application and local building code requirements. Always consult your local building official or Green Insulation's Representative for approved applications and restrictions.

System Specifications

<u>Viscosity</u>	<u>cps @ 70° F</u>
A- Component	175-250
B- Component	600-800

<u>Mix Ratio</u>	<u>By Volume</u>
A- Component	100
B- Component	100

Typical Physical Properties

Yield 4000-4500 board feet (Individual results may vary)

Density	ASTM D-1622	Nominal 1.8 – 2.0lbs/ft ³	
Yield	Board Feet	4,000 – 4,500	
Compressive Strength	ASTM D-1621	35 PSI	
Tensile Strength	ASTM D-1623	80 PSI	
Percent Closed Cells	ASTM D-2856	≤ 90%	
Insulation Values	ASTM C- 518	k factor	R value/Inch
		BTU-in/ft ² -°F-hr	ft ² -°F-hr/BTU-in
	Aged 180 days	0.151	6.62 Inch
Fungi Resistance	ASTM G- 21	Zero Rating	
Air Permeation	ASTM E -283 (At 75 PA)	Zero Air Leakage	
Dimensional Stability	ASTM D -2126	% Volume Change	
		158°F 100% Relative Humidity, 7 days	<8
		200°F, 7 days	<11
	-20°F, 7days	<1	
Surface Burning	ASTM E-84	Class 1	
Characteristics	(Nominal 5 inches)	≤ 25 flame spread/≤ 450 smoke	
Water Vapor			
Transmission	ASTM E-96	1.11 perm-inches	
Sound Transmission			
Class	ASTM E -90	Class 33	
VOC Testing	CAN/ULC-S774	Pass	

Saskatchewan Research Counsel

*Typical data is obtained from laboratory samples and values may vary under actual field conditions.

GIT's 2.0 is air impermeable at 75 Pa, as required in IRC 806.4 (2006). These flame spread ratings are not intended to reflect hazards presented by this or any other material under actual fire conditions.

Disclaimer: Information contained herein is, true and accurate, but all recommendations or suggestions are made without guarantee. Green Insulation Technology products are intended for sale to residential and commercial customers. Since Green Insulation Technology does not exercises control over it's customer appreciation or use of the product manufactured by Green Insulation Technology and since materials used with the products may vary, it is understood that Green Insulation Technology can warrant only that our products will meet our written specifications. Nothing herein shall constitute any warranty of merchantability or fitness, nor is protection from any low or patent to be inferred. All patent rights are reserved. Green Insulation Technology requests that customers inspect and test our products before use. And satisfy themselves as to contents and suitability. The exclusive remedy for all proven claims is replacement of our materials and in no event shall Green Insulation be liable for any consequential, incidental, indirect, or special damages resulting in any manner form the furnishing of the material.